

DESCRIPTION

Nukote XT is NCSI's primary coating for applications with extreme conditions like long-term wastewater immersion or applications with high chemical content. Nukote XT is a 100% solid, modified polyurea that displays outstanding physical properties with high microbial and bacteria resistance including anaerobic and aerobic microbial waste by-products.

FEATURES

- 100% solids with zero VOC
- Very high tensile strength and elongation
- Self-leveling
- Seamless, resilient, will not crack or check
- Resistant to microbial wastes
- Resistant to phosphates and alkalis
- Low permeability
- Fast reactivity and cure time with no catalysts
- Provides galvanic corrosion resistance
- Performs in constant temperatures from -30°C to 70°C
- Applicable in temperatures from -30°C to 135°C
- Almost immediate return-to-service times

TYPICAL USES

Nukote XT is designed for use on concrete, steel, or other substrates in immersion applications with water, wastewater, sewage, and high chemical content. Nukote XT can also be used as a protective, elastomeric membrane coating in:

- Manufacturing/Industrial facilities
- Food processing plants
- Canals, dams, and holding tanks
- Numerous marine applications
- Sewage processing equipment and tanks
- Primary/secondary containment for chemical processing

COLORS

Standard medium gray. Custom colors, blended to match any RAL number, are available upon request.

PACKAGING

Nukote XT is available in 38 liter kits shipped in plastic pails, 400 liter drum sets shipped in metal drums and 2090 tote sets shipped in hardened plastic, metal reinforced UN approved totes.

COVERAGE

Nukote XT may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mm thickness is one Liter per m².

SURFACE PREPARATION

For optimum performance, the substrate should be hydro or sand blasted. Concrete substrates should be allowed to cure a minimum of 30 days. On concrete, Nukote XT should always be applied over a suitable primer for maximum adhesion.

PHYSICAL PROPERTIES @ 24°C

Solids By Volume	100%
Volatile Organic Compounds	0 g/l
Theoretical Coverage @ 1000 Microns	1 m ² /L
Weight Per Liter in Kilograms	A:1.12 B:1.04
Viscosity (cps) @ 25 °C	A:550 to 650
Viscosity (cps) @ 25 °C	B:750 to 850
Shelf Life @ 10°C to 50°C	12 to 18
.....	Months
Tensile Strength @ 25°C ASTM D-412	>17
.....	N/mm ²
Elongation @ 25 °C ASTM D-412	350% to
.....	400%
Hardness (Shore D) ASTM D-2240	47 to 52
Flexibility 3mm mandrel ASTM D-1737	PASS
Tear Strength Die C ASTM D-624	>85 kN/m
Fire Rating UBC	Class 2
Flash Point Pensky-Martin	>93°C
Service Temperature Range-Dry	-30°C to
.....	135°C
Abrasion Resistance ASTM D-4060	<15 mg loss
Taber CS17 1000mg / 1000rev.	

PROCESSING PROPERTIES @125 MICRONS 24°C/54% RH

Gel Time (Adjustable)	10 to 20 sec.
Tack Free Time (125 microns)	30 to 125sec.
Post Cure Time	24 Hours
Volume Ratio (A:B)	1 to 1
Block Temperature	60°C to 70°C
Hose Temperatures (A and B)	60°C to 70°C
Constant Pressure	136 Bar

CLARIFICATION OF PROPERTY VALUES

The physical properties shown in the above table are defined in a range of values to allow for compliance when testing of sprayed films or laboratory draw down films. Results derived from independent testing will fall within the ranges shown if the testing performed complies with the standards utilized for each individual property shown. Results vary dependent on several factors, including: the equipment utilized, product mix ratios, application pressures, application temperatures, ambient temperatures, dry film thickness, age of the sample tested, etc. Results also vary dependent on the film type tested with laboratory draw down films deriving higher properties than sprayed films. Test results from films of at least 30-days in age will provide higher values than results from younger films as chemical cross-linking requires this time period to complete.

For some steel applications, a primer may not be necessary—please review your specific project with Nukote technicians. For all submersed applications, a primer is absolutely essential.

MIXING

Nukote XT must not be diluted under any circumstance. Use appropriate solvent for purge line and flushing of equipment and if spraying stops for a period of time in excess of the pot life of the material. Thoroughly mix Nukote XT part B resin material with air driven power equipment until a homogeneous mixture and color is obtained.

APPLICATION

This material may be applied utilizing high-pressure, heated plural component spray proportioning equipment, but it is designed to be applied using NCSI low pressure both hand held and full size application equipment.

After proper preparation, Nukote XT should be applied in a cross directional (North, South, East, and West) method. Recommended DFTs are a function of the project, please contact a Nukote technician. On horizontal surface applications, a texture “stipple” coat can be applied for non-skid purposes, after reaching the initial desired film thickness.

EQUIPMENT CLEANUP

Cured product may be disposed of without restriction. The un-cured isocyanate and resin portions should be mixed together and disposed of in a normal manner. “drip-free” containers should be disposed of according to local environmental laws and ordinances.

STORAGE

Twelve to eighteen months in factory delivered, unopened drums. Keep away from extreme heat, freezing, and moisture. The use of drum heaters is encouraged to reduce material viscosity at low temperatures.

LIMITATIONS

Do not open until ready to use, and store in a sealed container after opening. Adding a nitrogen blanket is strongly recommended.

WARNING

This product contains isocyanates and curatives.

CHEMICAL RESISTANCE

Each Nukote product formulation has varying levels of resistance to specific chemicals. Please review the chemical immersion test data included in the Nukote Test Book for general resistance to specific chemicals at specific concentration levels. Chemical concentrations are complex and when combined with temperatures above ambient levels this complexity increases exponentially. Contact Nukote technical personnel for specific recommendations for chemical resistance prior to specifying these products in this application type.

Please read all information in the general guidelines, product data sheets, guide specifications and material safety data sheets (MSDS) before applying material. Published technical data and instructions are subject to change without notice. Contact your local NCSI representative or visit our website for current technical data and instructions.

Nukote Coating Systems International, LLC has a general product warranty and project specific warranties. Both warranties are backed by years of industry experience and insurance policies with a multinational insurance company. For information on the general product warranty please see below or contact NCSI for more information. For project specific warranties, these are available on a case-by-case basis. NCSI technicians must sign off on the specification, and in most cases a NCSI technician will be onsite during application to inspect surface preparation and application. For more detailed warranty contact a NCSI office.

NCSI has a comprehensive training program for our qualified applicators and distributors. Please contact your local NCSI office or representative or visit our website for information on our training program or for current technical data and instructions.

LIMITED WARRANTY

NCSI warrants its products to be free of manufacturing defects. Polyurea and other multi-component products are technically manufactured at the time they are mixed. When mixed in accordance with NCSI guidelines, NCSI warrants the product will meet NCSI's technical specifications. NCSI warrants its products, when properly installed over a properly prepared substrate, will perform as designed and specified.

Unless otherwise stated in writing, NCSI's sole responsibility shall be to replace the defective product. There are no other warranties by NCSI of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. NCSI shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. NCSI shall not be responsible for use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature or physical movement of the substrate or structural defects are also excluded from the limited warranty. NCSI reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are neither guaranteed nor to be construed as a warranty, either expressed or implied.

It is the user's responsibility to satisfy themselves by their own, independent tests, to determine suitability of the product for their own intended use, application and job situation. The user assumes all risk and liability resulting from his use of the product. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a NCSI corporate officer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures.

Test performance results were obtained in a controlled environment and NCSI makes no claim that these tests or any other tests accurately represent all environments.